

## **Technical Data Sheet - ASTM Standard**

Stone type: Larvikite (Monzonite). Origin: Crafted 300 million years ago in Larvik, Norway.

## LUNDHS Marina®

LUNDHS Marina® is characterised by large steel-blue feldspar crystals. With large crystals and homogenous colour, it is perfect for large projects.

Technical Properties	Test Surface	Standard	Unit	Mean	
Apparent Density <sup>2)</sup>	Sawn	ASTM C97	lbs/ft³	170.00 ±	
Open Porosity <sup>1)</sup>	Sawn	NS-EN 1936	%	0.10 ±	
Water Absorption <sup>2]</sup>	Sawn	ASTM C97	% weight	0.01 ±	
Slip Resistance <sup>2)</sup>	Polished	ANSI A326.3	DCOF, wet	0.34 ±	
	Honed	ANSI A326.3	DCOF, wet	0.38 ±	
	Caress	ANSI A326.3	DCOF, wet	0.30 ±	
	Silk/Leather	ANSI A326.3	DCOF, wet	0.59 ±	
	Waterjet	ANSI A326.3	DCOF, wet	0.83 ±	
	Flamed	ANSI A326.3	DCOF, wet	0.77 ±	
	Sandblasted	ANSI A326.3	DCOF, wet	0.82 ±	
Abrasion Resistance Evaluation <sup>2)</sup>	Sawn	ASTM C1353	Index	182.70 ±	
Breaking Load at Dowel Holes <sup>1)</sup>	Sawn	NS-EN 13364	N	3713 ±	
Compressive Strength <sup>2)</sup>		ASTM C170	ASTM C170		
Perpendicular Loading, wet	Sawn	ASTM C170	psi	22,830 ±	
Perpendicular Loading, dry	Sawn	ASTM C170	psi	23,230 ±	
Parallel Loading, wet	Sawn	ASTM C170	psi	23,590 ±	
Parallel Loading, dry	Sawn	ASTM C170	psi	20,750 ±	
Flexural Strength, thickness 1¼" 2)		ASTM C880	ASTM C880		
Perpendicular Loading, wet	Sawn	ASTM C880	psi	2,090 ±	
Perpendicular Loading, dry	Sawn	ASTM C880	psi	1,970 ±	
Parallel Loading, wet	Sawn	ASTM C880	psi	1,930 ±	
Parallel Loading, dry	Sawn	ASTM C880	psi	2,030 ±	
Post Freeze-Thaw - 150 cycles <sup>2)</sup>		ASTM C666	ASTM C666		
Perpendicular Loading - no visual changes	Sawn	ASTM C666	psi	2,370 ±	
Parallel Loading - no visual changes	Sawn	ASTM C666	psi	1,920 ±	
Petrographic composition <sup>1)</sup>		NS-EN 12407			

Feltspar: 82%, Pyroxene: 3.5%, Nepheline: 2%, Amphibole: 3%, Opagues (magnetite, ilmenite): 3%, Biotite: 2.5%, Olivine: 2.5%, Apatite: 1.5%

<sup>1)</sup> The tests have been performed at SINTEF according to technical requirements given in e.g. NS-EN 1467 (rough blocks), NS-EN 1469 (slabs for cladding), NS-EN 12057 (modular tiles) and NS-EN 12058 (slabs for floors and stairs). Test results of petrographic composition are an average of tests performed by SINTEF in 2006 and 2019. Only main minerals are listed.

Test results are based on 3x2 cm objects and the examination provides information of the texture of the rock. However, variations in mineral composition and structure must be expected.

 $^{\mbox{\tiny 2)}}$  Tested at Natural Stone Institute according to ASTM and ANSI standard test methods.

Lundhs AS Kanalgata 59, NO-3263 Larvik, Norway Phone: +47 33 12 11 64 info@lundhs.no

NATURAL STONE FROM NORWAY lundhs.no / lundhsrealstone.com

